

PolyFoam™ FLOOR

March 2019

Polyfoam™ Floorboards

For floors and basements



Thickness (mm)	Thermal conductivity (W/mK)	Thermal resistance (m ² K/W)	Length (mm)	Width (mm)	Compressive strength (kPa)
Polyfoam Floorboard Standard					
25	0.033	0.75	2500	600	200
35	0.033	1.05	2500	600	200
50	0.033	1.50	2500	600	200
65	0.033	1.95	2500	600	200
75	0.033	2.25	2500	600	200
100*	0.033	3.00	1250	600	200
Polyfoam Floorboard Extra					
25	0.033	0.75	2500	600	300
35	0.033	1.05	2500	600	300
50	0.033	1.50	2500	600	300
60	0.033	1.80	2500	600	300
65	0.033	1.95	2500	600	300
75	0.033	2.25	2500	600	300
100*	0.033	3.00	1250	600	300
125*	0.033	3.75	1250	600	300
150*	0.033	4.50	1250	600	300

*Lap jointed board

Performance

The thermal conductivity of Polyfoam Floorboard Standard and Extra is 0.033W/mK

Benefits

- High compressive strength and protects the damp proof membrane from damage
- Highly resistant to water absorption
- Robust and can tolerate traffic from following trades

Certification

- British Board of Agrément Certificate
- Environmental Product Declaration
- BES 6001: Responsible Sourcing of Construction Products

Polyfoam XPS Limited
 Hunter House Industrial Estate,
 Hartlepool TS25 2BE
 Tel: 01429 855100
 Fax: 01429 868678
 info@polyfoamxps.co.uk

www.polyfoamxps.co.uk

© Polyfoam XPS 2018. All rights reserved.
 Polyfoam™ - Trademark of Polyfoam XPS Ltd

PolyFoam™ XPS

Polyfoam™ Floorboards

POL1001DAT - V0319

Description

Polyfoam Floorboard is a rigid, lightweight extruded polystyrene (XPS) insulation. Available in Standard, Extra and Super grades, it offers a range of compressive strengths for use in applications ranging from domestic floor slabs to intensively loaded industrial flooring.

In addition to lambda values as low as 0.033 W/mK, the thermally efficient foam boards are also robust and moisture resistant, making them suitable for basement walls and floors, swimming pool basins and perimeter insulation below DPC.

Application

Polyfoam Floorboards are suitable for almost any floor construction including:

- Below a concrete slab
- Below a screed
- Below chipboard

Basement walls

Polyfoam Floorboards can also be used as the external insulation layer in basement walls:

Basement depth up to 2.50m -

Polyfoam Floorboard Standard

Basement depth 2.50m to 5.00m -

Polyfoam Floorboard Extra

Durability

The continuous service temperature limit of Polyfoam Floorboards is up to +70° C.

Environmental

The BRE have approved and issued Environmental Product Declarations (EPDs) for the Polyfoam range of products in accordance with EN 15804:2012+A1:2013.

Polyfoam Floorboard Extra and Standard represents no known threat to the environment and has Zero Ozone Depletion Potential and a low Global Warming Potential. Polyfoam Roofboard Extra is non bio-degradable and 100% recyclable.

Responsible Sourcing

Polyfoam XPS Limited has been awarded a certificate of approval from BRE Global, stating that, having complied with requirements of BES 6001:issue 3.1, Polyfoam XPS Limited have achieved a performance rating of 'Pass' for the Polyfoam product range.

Compressive strength

Polyfoam Floorboards are highly resistant to compression and withstand both occasional and long term static loads. Load bearing construction elements should be designed to adequately support the combination of imposed and dead loads without creating excessive deflection.

Vapour resistivity

The water vapour resistivity of Polyfoam Floorboards is 625MNs/g.m when tested in accordance with BS EN 12086.

Moisture absorption

Polyfoam Floorboards have a moisture absorption of 0.6% by volume when tested in accordance with EN 12087 and can be laid in standing water or up against wet concrete with negligible impact on the performance of the product.

Handling and storage

Polyfoam Floorboards are lightweight and easy to handle and install. Polyfoam Floorboards are supplied in four sided packaging designed to be easily recognised and are labelled with identifying product and manufacturing data. Ensure the boards are not stored close to open flames or other ignition sources and avoid volatile organic compounds and chemicals such as solvents. Polyfoam Floorboards should not be left exposed to prolonged sunlight as this will result in surface degradation. When outside storage for extended periods is required cover the products with opaque/light coloured sheeting.

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work activities presented in this document is not permitted. The information contained in this document has been provided in good faith, however the publisher and editors cannot assume legal responsibility or any liability for incorrect information and the consequences thereof. It is the purchaser's responsibility to determine whether these Polyfoam XPS products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation.